

Intertek ETL Semko
ASTM D 1929
TEST RESULTS

Client: Standard ICF Corporation
Project No.: 3111685SAT-002
Date: 12/27/2006
SPECIMEN I.D. Polypropylene Web

Flash-Ignition Temperature: 360 °C (680 °F) Flaming

Spontaneous-Ignition Temperature: 390 °C (734 °F) Flaming